

optiprint[®] gingiva

Germany's favorite 3D Resin



Technische Daten / Technical data

Eigenschaft / property	Resultat / result	Methode / method
Shore A / shore A	> 55	DIN EN ISO 7619-1
Viskosität / viscosity (25 °C)	1880 mPas	Intern, Brookfield

22/2022



SDB/IFU