

# optiprint<sup>®</sup> guide

Germany's favorite 3D Resin



## Technische Daten / Technical data

Eigenschaft / property	Resultat / result	Methode / method
Biegemodul / flexural modulus	> 1600 MPa	DIN EN ISO 178
Biegefestigkeit / flexural strength	> 60 MPa	DIN EN ISO 178
Shore Härte / shore hardness	> 75 Shore D	DIN EN ISO 7619-1
Viskosität / viscosity (25 °C)	160 mPas	Intern, Brookfield

22/2022



SDB/IFU