

optiprint[®] model

Germany's favorite 3D Resin



Technische Daten / Technical data

Eigenschaft / property	Resultat / result	Methode / method
Biegemodul / flexural modulus	> 1600 MPa	DIN EN ISO 178
Biegefestigkeit / flexural strength	> 60 MPa	DIN EN ISO 178
Shore D / shore D	> 80	DIN EN ISO 7619-1
Viskosität / viscosity (25 °C)	1300 mPas	Intern, Brookfield

01/2022



SDB/IFU