

# VICTREX AM™ 200 FIL



## Product Description

High performance thermoplastic material, PolyArylEtherKetone (PAEK), semi crystalline, filament for Additive Manufacture by filament fusion and other melt extrusion 3D printing processes. Colour natural/beige.

## Typical Application Areas

Additive manufacturing processing. Filament Fusion printed parts, to achieve improved printed part strength and printability compared to PEEK polymer on most machines. For use in higher temperature applications and chemically aggressive environments. Low outgassing, suitable for sterilisation. Not suitable for medical implant applications. Product supplied vacuum packed with desiccant and dry when produced. Drying before use is recommended.

Dimension	Test Method	Units	Typical Value
Diameter	3 axis laser micrometer	mm	1.75
Linear density	Victrex test method VSH-STM-01	g/10000 m	31,000

Packaging	
Spool Dimensions	200mm diameter 70mm width 55mm centre bore
Spool Material	Heat-resistant Polycarbonate
Nominal Weights	1kg, 0.5 kg respectively
Nominal Lengths	322m, 161m respectively

Example Material Properties				Orientation		
	CONDITIONS	TEST METHOD	UNITS	XY	YZ	ZX
Tensile Strength	Yield, 23°C	ISO 527	MPa	65	70	45
Tensile Modulus	23°C	ISO 527	GPa	3.3	2.5	2.7
Tensile Elongation	Break, 23°C	ISO 527	%	15	15	5.0

Thermal Data					
Melting Point	DSC	ISO 11357	°C	303	
Glass Transition (Tg)	DSC (Onset)	ISO 11357	°C	151	
	DSC (Midpoint)	ISO 11357	°C	154	
Crystallisation Point	DSC	ISO 11357	°C	249	

Flow					
Melt Viscosity	400°C, 1000s <sup>-1</sup>	ISO 11443	Pa.s	245	

Example Processing Conditions	
Drying Temperature / Time	120°C / 5h (residual moisture <0.02%)
Extrusion Temperature	380-400°C (Nozzle)
Chamber/Build-Space Temperature	Printing directly semi-crystalline: Above 150°C (see note below) Printing amorphous: Below 150°C (see note below)
Bed Temperature	20-40°C above chamber temperature, keeping below 150°C for amorphous print.
Annealing conditions	Slow heating rate (3°C/min ramp rate). 170-180°C, 2-4 hours. Optimization may be required.

---

## Notes

Best results may be expected from elevated build-space temperatures and are machine specific. This datasheet represents properties that may be expected from build-space temperatures between 50-120°C. Samples have been successfully produced on <120°C build-space temperatures, however higher performance may be expected from machines with >120°C build space temperatures. Results vary widely from machine to machine.

Annealing may be required to generate semi-crystalline parts, depending on the machine and process conditions used in printing. Semi-crystalline parts can be made in some machines by using chamber temperatures >150°C, however in other machines the best results may be achieved by printing parts with reduced crystallinity and subsequently annealing. Annealing temperatures between 170-180°C are recommended. Parts may deform if higher annealing temperatures are used. Depending on the print parameters, annealing conditions may require adjustment for best results.

### Important notes:

1. Example values only. Not product specification.
2. Printing condition details are available on request.
3. Data are generated in accordance with prevailing national, international and internal standards, and should be used for material comparison. Actual property values are highly dependent on part geometry, equipment configuration, extrusion deposition strategy and processing conditions. Properties may also differ for along flow and across flow directions and from different printers technologies and manufacturers.

Detailed data are available on our website [www.victrex.com](http://www.victrex.com) or upon request.

---

### World Headquarters

Victrex plc  
Hillhouse International  
Thornton Cleveleys, Lancashire  
FY5 4QD, United Kingdom  
TEL +44 (0)1253 897700  
FAX +44 (0)1253 897701  
MAIL [victrexplc@victrex.com](mailto:victrexplc@victrex.com)



Victrex plc and/or its group companies ("Victrex plc") believes that the information contained in this document is an accurate description of the typical characteristics and/or uses of the product or products, but it is the customer's responsibility to thoroughly test the product in each specific application to determine its performance, efficacy, and safety for each end-use product, device or other application. Suggestions of uses should not be taken as inducements to infringe any particular patent. The information and data contained herein are based on information we believe reliable. Mention of a product in this document is not a guarantee of availability. Victrex plc reserves the right to modify products, specifications and/or packaging as part of a continuous program of product development. Victrex plc makes no warranties, express or implied, including, without limitation, a warranty of fitness for a particular purpose or of intellectual property non-infringement, including, but not limited to patent non-infringement, which are expressly disclaimed, whether express or implied, in fact or by law. Further, Victrex plc makes no warranty to your customers or agents, and has not authorized anyone to make any representation or warranty other than as provided above. Victrex plc shall in no event be liable for any general, indirect, special, consequential, punitive, incidental or similar damages, including without limitation, damages for harm to business, lost profits or lost savings, even if Victrex has been advised of the possibility of such damages regardless of the form of action. VICTREX™, APTIV™, VICOTE™, VICTREX PIPES™, VICTREX HT™, VICTREX ST™, VICTREX WG™, PEEK-ESD™ and the Triangle (Device), are trademarks of Victrex plc or its group companies.