



Saremco print CROWNTEC

Technical Data

Consistency	middle viscos homogeneous liquid
Colour	According to Vita Shades (A1, A2, A3, A3.5, B1, Snow White (Bleach))
Depth of cure (DIN EN ISO 4049)	≥ 1,5 mm
Flexural strength (DIN EN ISO 4049)	> 130 MPa
E-Modulus (DIN EN ISO 4049)	> 4000 MPa
Barcol-Hardness	> 40
Shelf-life	3 years